



Technical Data Sheet

DOWSIL™ 817 Mirror Adhesive

High modulus neutral silicone sealant

Features & Benefits

- Non-corrosive, odorless, ready to use gun grade sealant which reacts with air moisture
- Excellent unprimed adhesion on most glasses, metals and mirror coatings
- Outstanding resistance to heat and humidity
- Resistant to ozone, ultra-violet radiation and temperature extremes

Applications

- DOWSIL™ 817 Mirror Adhesive is a one-part silicone sealant for internal fixation of mirrors, coated glass or metal panels onto various substrates and for bonding of glass and back plate in solar thermal panels

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

| Test ¹ | Property | Unit | Result |
|-------------------|---|----------|----------------------------|
| | Cure system | | Neutral |
| | Application temperature | °C °F | +5 to +40 +41 to +104 |
| | Service temperature range | °C °F | -50 to +100 -58 to +212 |
| | Working time | minutes | 29 |
| CTM97B | Specific gravity | g/ml | 1.43 |
| CTM062 | Slump | mm | < 3 |
| | 12*12*50 mm size T.A. joint (ISO² 8339) | | |
| CTM99E | Hardness (Shore A) | | 38 |
| | Young modulus | MPa | 1.2 |

1. CTM: Corporate Test Method, copies of CTMs are available on request.
2. ISO: International Standardization Organization

How To Use

Surface Preparation

Ensure that surfaces to be sealed are clean, dry, sound and free from grease, dust and other contaminants which could impair adhesion. Surfaces can be cleaned and degreased by wiping with a suitable solvent such as DOWSIL™ R-40 Universal Cleaner on a clean oil and lint-free cloth before application of sealant. Check to ensure that the mirror has been evenly coated, is protected by lacquer and is free of scratches.

Note: When using any solvent, always provide adequate ventilation. Avoid heat, sparks and open flames. Use solvent resistant gloves. Observe and follow all precautions listed on solvent container label.

Priming

For specific advice, please refer to our Primers' Guide.

Sealant Application

The sealant is ready to use. Apply 10 mm wide strips vertically on the back of the mirror in 100 mm intervals. Then press the mirror onto the surface, preserving a constant bead thickness of 2 mm for optimum cure and mechanical grab. Support the mirror for a minimum of 24 hours using adhesive tapes. This will ensure good contact and a minimum of displacement. Air should be allowed to circulate freely around the edges of the mirror thereby allowing the sealant to cure.

Clean-up

Excess sealant may be cleaned off tools and non-porous surfaces whilst in an uncured state using DOWSIL R-40 Universal Cleaner. If sealant is misapplied to porous substrates, it should be left until just cured, and then removed by peeling, cutting or other mechanical means. Care should be taken not to damage plastic or coated surfaces.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life And Storage

When stored in cool, dry conditions below 30°C (86°F) in the original unopened containers, DOWSIL 817 Mirror Adhesive has a usable life of 12 months from the date of production.

Packaging Information

DOWSIL 817 Mirror Adhesive is supplied in 310 ml cartridges packed in boxes of 12.

Limitations

Do not use DOWSIL 817 Mirror Adhesive on bituminous substrates, substrates based on natural rubber, chloroprene or EPDM or on building materials which might bleed oils, plasticizers or solvents. Do not use DOWSIL 817 Mirror Adhesive in a totally confined space because the sealant requires atmospheric moisture to cure. DOWSIL 817 Mirror Adhesive is not recommended for use in submerged applications or in applications where physical abuse of abrasion is likely to occur.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 817 Mirror Adhesive

© 2017 The Dow Chemical Company. All rights reserved.

Limitations (Cont.)

When used with safety mirrors (single pane mirrors laminated with a plastic film at the back to prevent shattering of the glass when broken), first check adherence of DOWSIL 817 Mirror Adhesive on the plastic film.

This product is not suitable for areas where food contact is likely.

DOWSIL 817 Mirror Adhesive is not recommended for structural glazing or insulated glazing applications.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

<http://www.consumer.dow.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

